

KPS HV, Large Case, SM Series, X7R Dielectric, 500 – 10,000 VDC (Industrial Grade)

Overview

KPS HV (KEMET Power Solutions, High Voltage), Large Case (≥ 1515), SM Series capacitors in X7R dielectric are designed to meet robust performance standards required in higher reliability industrial applications. Utilizing lead-frame technology, SM Series devices isolate the multilayer ceramic chip component from the printed circuit board providing advanced mechanical and thermal stress performance. Isolation of the chip component also addresses concerns for audible, microphonic noise that may occur when a bias voltage is applied. Although this technology does not eliminate the potential for mechanical damage that may propagate during extreme environmental and handling conditions, it does demonstrate superior performance over non-isolating systems. Available in both formed "L" and "J" lead configurations, SM Series devices offer up to


10 mm of board flex capability and exhibit lower ESR, ESL and higher current discharge capability when compared to other dielectric solutions.

Combined with the stability of an X7R dielectric, KEMET's High Voltage SM Series devices exhibit a predictable change in capacitance with respect to time and voltage and boast a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to $\pm 15\%$ from -55°C to $+125^{\circ}\text{C}$.

KEMET's Industrial grade products offer additional screening options for higher reliability applications. Both Group A and Group B testing/inspection options per MIL-PRF-49467 are available for the SM Series.

Benefits

- -55°C to $+125^{\circ}\text{C}$ operating temperature range
- Large Case Sizes (≥ 1515)
- Formed "L" or "J" leadframe configurations
- Group A and B screening per MIL-PRF-49467 available
- Reliable and robust leadframe termination system
- DC voltage ratings of 500 V, 1 KV, 2 KV, 3 KV, 4 KV, 5 KV, 7.5 KV, and 10 KV
- Capacitance offerings ranging from 150 pF up to 5.6 μF




Ordering Information

SM20		B	153	K	501	B	M
Style/Size		Dielectric	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Lead Configuration ¹	Testing/ Inspection Option ²
SM20	SM30	B = X7R	Two significant digits and number of zeros	K = $\pm 10\%$ M = $\pm 20\%$	501 = 500	A = Formed "L" B = Formed "J"	Blank = None M = Group A per MIL-PRF-49467
SM21	SM31				102 = 1,000		
SM22	SM33				202 = 2,000		
SM23	SM34				302 = 3,000		
SM24	SM35				402 = 4,000		
SM25	SM36				502 = 5,000		
SM26					752 = 7,500		
		103 = 10,000					

¹ Standard lead configuration is formed "J". If the appropriate character is excluded from the ordering code, the assumed lead configuration will be formed "J".

² Group B testing/inspection option per MIL-PRF-49467 is available upon request. Please contact KEMET for ordering details.

Dimensions – Inches (Millimeters)



Style/ Size	L Length	W Width	T Thickness Max.	A Lead Width Max.	LL Lead Length (Formed "L")	LL Lead Length (Formed "J")	
SM20	0.150±0.015 (3.81±0.38)	0.150±0.015 (3.81±0.38)	0.130 (3.30)	0.100 (2.54)	0.100±0.020 (2.54±0.51)	0.040±0.010 (1.02±0.25)	
SM21	0.200±0.020 (5.08±0.51)	0.200±0.020 (5.08±0.51)	0.180 (4.57)				
SM22	0.250±0.020 (6.35±0.51)	0.200±0.020 (5.08±0.51)	0.220 (5.59)	0.200 (5.08)			
SM23	0.350±0.030 (8.89±0.76)	0.300±0.030 (7.62±0.76)		0.300 (7.62)			
SM24	0.450±0.030 (11.43±0.76)	0.400±0.030 (10.20±0.76)		0.400 (10.20)			
SM25	0.550±0.030 (14.00±0.76)	0.500±0.030 (12.70±0.76)	0.140 (3.55)	0.500 (12.70)		0.100±0.020 (2.54±0.51)	0.100±0.020 (2.54±0.51)
SM26	0.650±0.030 (16.50±0.76)	0.600±0.030 (15.20±0.76)		0.100 (2.54)			
SM30	0.300±0.030 (7.62±0.76)	0.150±0.015 (3.81±0.38)	0.130 (3.30)	0.200 (5.08)			
SM31	0.400±0.030 (10.20±0.76)	0.200±0.020 (5.08±0.51)	0.180 (4.57)				
SM33	0.700±0.030 (17.08±0.76)	0.300±0.030 (7.62±0.76)	0.220 (5.59)	0.300 (7.62)			
SM34	0.900±0.030 (22.90±0.76)	0.400±0.030 (10.20±0.76)		0.400 (10.2)			
SM35	1.100±0.030 (27.90±0.76)	0.500±0.030 (12.70±0.76)		0.500 (12.7)			
SM36	1.350±0.030 (33.00±0.76)	0.600±0.030 (15.20±0.76)					

Benefits cont'd

- Advanced protection against thermal and mechanical stress
- Provides up to 10 mm of board flex capability
- Reduces audible, microphonic noise
- Low ESR and ESL
- Non-polar device, minimizing installation concerns
- Silver plated copper alloy leadframe termination system

Applications

Typical applications include switch mode power supplies (input filters, resonators, tank circuits, snubber circuits, output filters), high voltage coupling and DC blocking, voltage multiplier circuits, DC/DC converters and coupling capacitors in Ćuk converters, noise reduction (piezoelectric/mechanical), circuits with a direct battery or power source connection, critical and safety relevant circuits without (integrated) current limitation and any application that is subject to high levels of board flexure or temperature cycling. Markets include power supply, LCD fluorescent backlight ballasts, HID lighting, telecom equipment, industrial and medical equipment/control and Military.

Qualification/Certification

Industrial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 3, Performance & Reliability.

Environmental Compliance

RoHS Compliant with Exemption(s).

Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	±15%
Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
Dielectric Withstanding Voltage (DWV)	150% of rated voltage for voltage rating of ≤ 1,250 VDC 120% of rated voltage for voltage rating of > 1,250 VDC (5±1 seconds and charge/discharge not exceeding 50 mA)
Dissipation Factor (DF) Maximum Limit at 25°C	2.5%
Insulation Resistance (IR) Limit at 25°C	1,000 megohm microfarads or 100 GΩ (Rated voltage DC applied for 120±5 seconds at 25°C for voltage rating of ≤ 500 VDC) (500 VDC applied for 120±5 seconds at 25°C for voltage rating of > 500 VDC)

Regarding aging rate: Capacitance measurements (including tolerance) are indexed to a referee time of 1,000 hours.

To obtain IR limit, divide MΩ-μF value by the capacitance and compare to GΩ limit. Select the lower of the two limits.

Capacitance and dissipation factor (DF) measured under the following conditions:

1 kHz ±50 Hz and 1.0 Vrms ±0.2 V if capacitance > 100 pF

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

Post Environmental Limits

High Temperature Life, Biased Humidity, Moisture Resistance				
Dielectric	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift
X7R	All	All	3.0	±20%

Table 1A – Capacitance Range/Selection Waterfall SM20 – SM24 Style/Size

Style/Size	SM20		SM21				SM22				SM23				SM24					Capacitance Tolerance				
Dimensions – inches (mm)																								
Length	0.150 ± 0.015 (3.81 ± 0.38)		0.200 ± 0.020 (5.08 ± 0.51)				0.250 ± 0.020 (6.35 ± 0.51)				0.350 ± 0.030 (8.89 ± 0.76)				0.450 ± 0.030 (11.43 ± 0.76)									
Width	0.150 ± 0.015 (3.81 ± 0.38)		0.200 ± 0.020 (5.08 ± 0.51)				0.200 ± 0.020 (5.08 ± 0.51)				0.300 ± 0.030 (7.62 ± 0.76)				0.400 ± 0.030 (10.20 ± 0.76)									
Thickness Maximum	0.130 (3.30)		0.180 (4.57)				0.180 (4.57)				0.220 (5.59)				0.220 (5.59)									
Lead Width Maximum	0.100 (2.54)		0.100 (2.54)				0.100 (2.54)				0.200 (5.08)				0.300 (7.62)									
Lead Length "L"	0.100 ± 0.020 (2.54 ± 0.51)		0.100 ± 0.020 (2.54 ± 0.51)				0.100 ± 0.020 (2.54 ± 0.51)				0.100 ± 0.020 (2.54 ± 0.51)				0.100 ± 0.020 (2.54 ± 0.51)									
Lead Length "J"	0.040 ± 0.010 (1.02 ± 0.25)		0.040 ± 0.010 (1.02 ± 0.25)				0.040 ± 0.010 (1.02 ± 0.25)				0.100 ± 0.020 (2.54 ± 0.51)				0.100 ± 0.020 (2.54 ± 0.51)									
X7R Dielectric																								
Voltage Code	501	102	202	501	102	202	302	501	102	202	302	501	102	202	302	402	501	102	202	302	402	502	Capacitance Tolerance	
Voltage DC	500	1 K	2 K	500	1 K	2 K	3 K	500	1 K	2 K	3 K	500	1 K	2 K	3 K	4 K	500	1 K	2 K	3 K	4 K	5 K		
Capacitance	Capacitance Code																						K, M	
330 pF	331	331	331																					
390 pF	391	391	391																					
470 pF	471	471	471																					
560 pF	561	561	561																					
680 pF	681	681	681					681	681	681	681													
820 pF	821	821	821	821	821	821	821	821	821	821	821													
1,000 pF	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102		102
1,200 pF	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122		122
1,500 pF	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152		152
1,800 pF	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182		182
2,200 pF	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222		222
2,700 pF	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272		272
3,300 pF	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332		332
3,900 pF	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392		392
4,700 pF	472	472		472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472		472
5,600 pF	562	562		562	562	562		562	562	562	562	562	562	562	562	562	562	562	562	562	562	562		562
6,800 pF	682	682		682	682	682		682	682	682		682	682	682	682	682	682	682	682	682	682	682		682
8,200 pF	822	822		822	822	822		822	822	822		822	822	822	822		822	822	822	822	822	822		822
0.01 µF	103	103		103	103	103		103	103	103		103	103	103	103		103	103	103	103	103	103		103
0.012 µF	123	123		123	123	123		123	123	123		123	123	123	123		123	123	123	123	123	123	123	
0.015 µF	153	153		153	153			153	153	153		153	153	153	153		153	153	153	153				
0.018 µF	183	183		183	183			183	183			183	183	183			183	183	183	183				
0.022 µF	223	223		223	223			223	223			223	223	223			223	223	223	223				
0.027 µF	273			273	273			273	273			273	273	273			273	273	273	273				
0.033 µF	333			333	333			333	333			333	333	333			333	333	333	333				
0.039 µF	393			393	393			393	393			393	393				393	393	393					
0.047 µF	473			473	473			473	473			473	473				473	473	473					
0.056 µF	563			563	563			563	563			563	563				563	563	563					
0.068 µF	683			683	683			683	683			683	683				683	683	683					
0.082 µF	823			823				823	823			823	823				823	823	823					
0.1 µF				104				104	104			104	104				104	104	104					
0.12 µF				124				124				124	124				124	124						
0.15 µF				154				154				154	154				154	154						
0.18 µF				184				184				184	184				184	184						
0.22 µF								224				224	224				224	224						
0.27 µF								274					274					274	274					
0.33 µF												334					334	334						
0.39 µF												394					394	394						
0.47 µF												474					474	474						
0.56 µF												564						564						
0.68 µF																	684							
0.82 µF																	824							
1.0 µF																	105							
1.2 µF																	125							

Table 1B – Capacitance Range/Selection Waterfall SM25 – SM31 Style/Size

Style/Size	SM25						SM26						SM30						SM31						Capacitance Tolerance
Dimensions – inches (mm)																									
Length	0.550 ± 0.030 (14.00 ± 0.76)						0.650 ± 0.030 (16.50 ± 0.76)						0.300 ± 0.030 (7.62 ± 0.76)						0.400 ± 0.030 (10.20 ± 0.76)						
Width	0.500 ± 0.030 (12.70 ± 0.76)						0.600 ± 0.030 (15.20 ± 0.76)						0.150 ± 0.015 (3.81 ± 0.38)						0.200 ± 0.020 (5.08 ± 0.51)						
Thickness Maximum	0.220 (5.59)						0.220 (5.59)						0.140 (3.55)						0.130 (3.30)						
Lead Width Maximum	0.400 (10.20)						0.500 (12.70)						0.100 (2.54)						0.100 (2.54)						
Lead Length "L"	0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						
Lead Length "J"	0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						0.100 ± 0.020 (2.54 ± 0.51)						
X7R Dielectric																									
Voltage Code	501	102	202	302	402	502	501	102	202	302	402	502	501	102	202	302	402	501	102	202	302	402	502	Capacitance Tolerance	
Voltage DC	500	1 K	2 K	3 K	4 K	5 K	500	1 K	2 K	3 K	4 K	5 K	500	1 K	2 K	3 K	4 K	500	1 K	2 K	3 K	4 K	5 K		
Capacitance	Capacitance Code																								
150 pF																		151	151	151	151	151			
180 pF																		181	181	181	181	181			
220 pF																		221	221	221	221	221			
270 pF																		271	271	271	271	271			
330 pF																		331	331	331	331	331			
390 pF																		391	391	391	391	391			
470 pF																		471	471	471	471	471			
560 pF																		561	561	561	561	561			
680 pF																		681	681	681	681	681	681	681	
820 pF																		821	821	821	821	821	821	821	
1,000 pF																		102	102	102	102	102			
1,200 pF																		122	122	122	122	122			
1,500 pF																		152	152	152	152	152	152	152	
1,800 pF																		182	182	182	182				
2,200 pF																		222	222	222	222	222			
2,700 pF	272	272	272	272	272	272	272	272	272	272								272	272	272	272	272	272	272	
3,300 pF	332	332	332	332	332	332	332	332	332	332								332	332	332	332	332	332	332	
3,900 pF	392	392	392	392	392	392	392	392	392	392								392	392	392	392	392	392	392	
4,700 pF	472	472	472	472	472	472	472	472	472	472	472	472						472	472	472	472	472	472	472	
5,600 pF	562	562	562	562	562	562	562	562	562	562	562	562						562	562	562	562	562	562	562	
6,800 pF	682	682	682	682	682	682	682	682	682	682	682	682						682	682	682	682	682	682	682	
8,200 pF	822	822	822	822	822	822	822	822	822	822	822	822						822	822	822	822	822	822	822	
0.01 µF	103	103	103	103	103	103	103	103	103	103	103	103						103	103	103	103	103	103	103	
0.012 µF	123	123	123	123	123													123	123	123	123	123	123	123	
0.015 µF	153	153	153	153	153													153	153	153	153	153	153	153	
0.018 µF	183	183	183	183														183	183	183	183	183	183	183	
0.022 µF	223	223	223	223														223	223	223	223	223	223	223	
0.027 µF	273	273	273	273														273	273	273	273	273	273	273	
0.033 µF	333	333	333	333														333	333	333	333	333	333	333	
0.039 µF	393	393	393	393														393	393	393	393	393	393	393	
0.047 µF	473	473	473	473														473	473	473	473	473	473	473	
0.056 µF	563	563	563															563	563	563	563	563	563	563	
0.068 µF	683	683	683															683	683	683	683	683	683	683	
0.082 µF	823	823	823															823	823	823	823	823	823	823	
0.1 µF	104	104	104															104	104	104	104	104	104	104	
0.12 µF	124	124	124															124	124	124	124	124	124	124	
0.15 µF	154	154																154	154	154	154	154	154	154	
0.18 µF	184	184																184	184	184	184	184	184	184	
0.22 µF	224	224																224	224	224	224	224	224	224	
0.27 µF	274	274																274	274	274	274	274	274	274	
0.33 µF	334	334																334	334	334	334	334	334	334	
0.39 µF	394	394																394	394	394	394	394	394	394	
0.47 µF	474	474																474	474	474	474	474	474	474	
0.56 µF	564																	564	564	564	564	564	564	564	
0.68 µF	684																	684	684	684	684	684	684	684	
0.82 µF	824																	824	824	824	824	824	824	824	

Table 1B – Capacitance Range/Selection Waterfall SM25 – SM31 Style/Size cont'd

Style/Size	SM25					SM26					SM30					SM31									
Dimensions – inches (mm)																									
Length	0.550 ± 0.030 (14.00 ± 0.76)					0.650 ± 0.030 (16.50 ± 0.76)					0.300 ± 0.030 (7.62 ± 0.76)					0.400 ± 0.030 (10.20 ± 0.76)									
Width	0.500 ± 0.030 (12.70 ± 0.76)					0.600 ± 0.030 (15.20 ± 0.76)					0.150 ± 0.015 (3.81 ± 0.38)					0.200 ± 0.020 (5.08 ± 0.51)									
Thickness Maximum	0.220 (5.59)					0.220 (5.59)					0.140 (3.55)					0.130 (3.30)									
Lead Width Maximum	0.400 (10.20)					0.500 (12.70)					0.100 (2.54)					0.100 (2.54)									
Lead Length "L"	0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)									
Lead Length "J"	0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)					0.100 ± 0.020 (2.54 ± 0.51)									
X7R Dielectric																									
Voltage Code	501	102	202	302	402	502	501	102	202	302	402	502	501	102	202	302	402	501	102	202	302	402	502	Capacitance Tolerance	
Voltage DC	500	1 K	2 K	3 K	4 K	5 K	500	1 K	2 K	3 K	4 K	5 K	500	1 K	2 K	3 K	4 K	500	1 K	2 K	3 K	4 K	5 K		
Capacitance	Capacitance Code																								
1.0 µF	105						105	105																K, M	
1.2 µF	125						125																		
1.5 µF	155						155																		
1.8 µF	185						185																		
2.2 µF							225																		
2.7 µF							275																		
2.9 µF							295																		

Table 1C – Capacitance Range/Selection Waterfall SM33 – SM35 Style/Size

Style/Size	SM33								SM34								SM35								Capacitance Tolerance
Dimensions – inches (mm)																									
Length	0.700 ± 0.030 (17.08 ± 0.76)								0.900 ± 0.030 (22.90 ± 0.76)								1.100 ± 0.030 (27.90 ± 0.76)								
Width	0.300 ± 0.030 (7.62 ± 0.76)								0.400 ± 0.030 (10.20 ± 0.76)								0.500 ± 0.030 (12.70 ± 0.76)								
Thickness Maximum	0.180 (4.57)								0.220 (5.59)								0.220 (5.59)								
Lead Width Maximum	0.200 (5.08)								0.300 (7.62)								0.400 (10.2)								
Lead Length "L"	0.100 ± 0.020 (2.54 ± 0.51)								0.100 ± 0.020 (2.54 ± 0.51)								0.100 ± 0.020 (2.54 ± 0.51)								
Lead Length "J"	0.100 ± 0.020 (2.54 ± 0.51)								0.100 ± 0.020 (2.54 ± 0.51)								0.100 ± 0.020 (2.54 ± 0.51)								
X7R Dielectric																									
Voltage Code	501	102	202	302	402	502	752	501	102	202	302	402	502	752	103	501	102	202	302	402	502	752	103	Capacitance Tolerance	
Voltage DC	500	1 K	2 K	3 K	4 K	5 K	7.5 K	500	1 K	2 K	3 K	4 K	5 K	7.5 K	10 K	500	1 K	2 K	3 K	4 K	5 K	7.5 K	10 K		
Capacitance	Capacitance Code																								
820 pF	821	821	821	821	821	821	821																		
1,000 pF	102	102	102	102	102	102	102	102	102	102	102	102	102	102	102									102	
1,200 pF	122	122	122	122	122	122	122	122	122	122	122	122	122	122	122									122	
1,500 pF	152	152	152	152	152	152	152	152	152	152	152	152	152	152	152									152	
1,800 pF	182	182	182	182	182	182	182	182	182	182	182	182	182	182	182									182	
2,200 pF	222	222	222	222	222	222	222	222	222	222	222	222	222	222	222									222	
2,700 pF	272	272	272	272	272	272	272	272	272	272	272	272	272	272	272									272	
3,300 pF	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	332	
3,900 pF	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	392	
4,700 pF	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	472	
5,600 pF	562	562	562	562	562	562		562	562	562	562	562	562	562	562	562	562	562	562	562	562	562	562	562	
6,800 pF	682	682	682	682	682	682		682	682	682	682	682	682	682	682	682	682	682	682	682	682	682	682	682	
8,200 pF	822	822	822	822	822			822	822	822	822	822	822	822					822	822	822	822	822	822	
0.01 µF	103	103	103	103	103			103	103	103	103	103	103	103					103	103	103	103	103	103	
0.012 µF	123	123	123	123	123			123	123	123	123	123	123	123					123	123	123	123	123	123	
0.015 µF	153	153	153	153				153	153	153	153	153	153	153					153	153	153	153	153	153	
0.018 µF	183	183	183	183				183	183	183	183	183	183	183					183	183	183	183	183	183	
0.022 µF	223	223	223	223				223	223	223	223	223	223	223					223	223	223	223	223	223	
0.027 µF	273	273	273	273				273	273	273	273	273	273	273					273	273	273	273	273	273	
0.033 µF	333	333	333	333				333	333	333	333	333	333	333					333	333	333	333	333	333	
0.039 µF	393	393	393	393				393	393	393	393								393	393	393	393	393	393	
0.047 µF	473	473	473					473	473	473	473								473	473	473	473	473	473	
0.056 µF	563	563	563					563	563	563	563								563	563	563	563	563	563	
0.068 µF	683	683	683					683	683	683	683								683	683	683	683	683	683	
0.082 µF	823	823	823					823	823	823	823								823	823	823	823	823	823	
0.1 µF	104	104						104	104	104									104	104	104	104			
0.12 µF	124	124						124	124	124									124	124	124				
0.15 µF	154	154						154	154	154									154	154	154				
0.18 µF	184	184						184	184	184									184	184	184				
0.22 µF	224	224						224	224	224									224	224	224				
0.27 µF	274	274						274	274	274									274	274	274				
0.33 µF	334	334						334	334										334	334					
0.39 µF	394	394						394	394										394	394					
0.47 µF	474	474						474	474										474	474					
0.56 µF	564	564						564	564										564	564					
0.68 µF	684	684						684	684										684	684					
0.82 µF	824							824	824										824	824					
1.0 µF	105							105	105										105	105					
1.2 µF	125							125											125	125					
1.5 µF	155							155											155						
1.8 µF								185											185						
2.2 µF								225											225						
2.7 µF																			275						
2.9 µF																			295						
3.3 µF																			335						
3.9 µF																			395						

Table 1D – Capacitance Range/Selection Waterfall SM36 Style/Size

Style/Size	SM36								Capacitance Tolerance
Dimensions – inches (mm)									
Length	1.350 ± 0.030 (33.00 ± 0.76)								K, M, P, Z
Width	0.600 ± 0.030 (15.20 ± 0.76)								
Thickness Maximum	0.220 (5.59)								
Lead Width Maximum	0.500 (12.7)								
Lead Length "L"	0.100 ± 0.020 (2.54 ± 0.51)								
Lead Length "J"	0.100 ± 0.020 (2.54 ± 0.51)								
X7R Dielectric									
Voltage Code	501	102	202	302	402	502	752	103	Capacitance Tolerance
Voltage DC	500	1 K	2 K	3 K	4 K	5 K	7.5 K	10 K	
Capacitance	Capacitance Code								
1,500 pF								152	K, M, P, Z
1,800 pF								182	
2,200 pF								222	
2,700 pF								272	
3,300 pF								332	
3,900 pF								392	
4,700 pF	472	472	472	472	472	472	472	472	
5,600 pF	562	562	562	562	562	562	562	562	
6,800 pF	682	682	682	682	682	682	682	682	
8,200 pF	822	822	822	822	822	822	822	822	
0.01 µF	103	103	103	103	103	103	103	103	
0.012 µF	123	123	123	123	123	123	123		
0.015 µF	153	153	153	153	153	153	153		
0.018 µF	183	183	183	183	183	183	183	183	
0.022 µF	223	223	223	223	223	223	223		
0.027 µF	273	273	273	273	273	273			
0.033 µF	333	333	333	333	333	333			
0.039 µF	393	393	393	393	393				
0.047 µF	473	473	473	473	473				
0.056 µF	563	563	563	563	563				
0.068 µF	683	683	683	683	683				
0.082 µF	823	823	823	823					
0.1 µF	104	104	104	104					
0.12 µF	124	124	124	124					
0.15 µF	154	154	154	154					
0.18 µF	184	184	184						
0.22 µF	224	224	224						
0.27 µF	274	274	274						
0.33 µF	334	334	334						
0.39 µF	394	394							
0.47 µF	474	474							
0.56 µF	564	564							
0.68 µF	684	684							
0.82 µF	824	824							
1.0 µF	105	105							
1.2 µF	125	125							
1.5 µF	155	155							
1.8 µF	185	185							
2.2 µF	225	225							
2.7 µF	275								
2.9 µF	295								
3.3 µF	335								
3.9 µF	395								
4.7 µF	475								
5.6 µF	565								

Table 2 – Chip Thickness/Packaging Quantities

Series	Style/Size	Tray Quantity Minimum ¹	Tray Quantity Maximum ¹
SM	SM20	1	50
	SM21		
	SM22		
	SM23		
	SM24		
	SM25		
	SM26		
	SM30		
	SM31		
	SM33		25
	SM34		10
	SM35		
	SM36		

¹ Minimum order value applies. Contact KEMET for details.

Soldering Process

The capacitors and assemblies outlined in this specification sheet are susceptible to thermal shock damage due to their large ceramic mass. Temperature profiles used should provide adequate temperature rise and cool-down time to prevent damage from thermal shock. In general, KEMET recommends against hand soldering for these types of large ceramic devices.

Recommended Soldering Technique:

- Solder reflow only

Preheating and Reflow Profile Notes:

Due to differences in the coefficient of thermal expansion for the different materials of construction, it is critical to monitor and control the heating and cooling rates during the soldering process. During the reflow soldering process, the maximum recommended heating and cooling rate (dT/dt) is 4°C/second. To ensure optimal component reliability, KEMET's recommended heating and cooling rate is 2°C/second. After soldering, the capacitors should be air cooled to room temperature before further processing. Forced air cooling is not recommended.

Recommended Reflow Soldering Profile:

Profile Feature	SnPb Assembly
Preheat/Soak	
Temperature Minimum (T_{smin})	100°C
Temperature Maximum (T_{smax})	150°C
Time (t_s) from T_{smin} to T_{smax}	60 – 90 seconds
Ramp-up Rate (T_L to T_p)	2°C/seconds
Liquidous Temperature (T_L)	183°C
Time Above Liquidous (t_L)	95 seconds
Peak Temperature (T_p)	240°C
Time within 5°C of Maximum Peak Temperature (t_p)	5 seconds
Ramp-down Rate (T_p to T_L)	2°C/seconds
Time 25°C to Peak Temperature	3.5 minutes

Note 1: All temperatures refer to the center of the package, measured on the package body surface that is facing up during assembly reflow.





Table 3 – Performance & Reliability: Test Methods and Conditions

Stress	Reference	Test or Inspection Method
Board Flex	JIS-C-6429	Appendix 2, Note: 2 mm (minimum) for all except 3 mm for COG.
Solderability	J-STD-002	Magnification 50 X. Conditions:
		a) Method B, 4 hours at 155°C, dry heat at 235°C
		b) Method B at 215°C category 3
		c) Method D, category 3 at 260°C
		1,000 cycles (-55°C to +125°C). Measurement at 24 hours +/-2 hours after test conclusion.
Biased Humidity	MIL-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and 300 VDC Maximum Add 100 K ohm resistor. Measurement at 24 hours +/-2 hours after test conclusion.
		Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours +/-2 hours after test conclusion.
		t = 24 hours/cycle. Steps 7a and 7b not required. Unpowered. Measurement at 24 hours +/-2 hours after test conclusion.
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of cycles required – 300. Maximum transfer time – 20 seconds. D14 dwell time – 15 minutes. Air – Air.
High Temperature Life	MIL-STD-202 Method 108 /EIA -198	1,000 hours at 125°C (85°C for X5R, Z5U and Y5V) with rated voltage applied.
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC, for 1,000 hours.
Vibration	MIL-STD-202 Method 204	5 g for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8 "X5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10–2,000 Hz.
Resistance to Soldering Heat	MIL-STD-202 Method 210	Condition B. No preheat of samples. Note: single wave solder – procedure 2.
Terminal Strength	MIL-STD-202 Method 211	Conditions A (2.3 kg or 5 lbs).
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condition F.
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical, OKEM Clean or equivalent.

Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature—reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.

Construction



Product Marking

Product marking is an extra-cost option. These devices will be supplied unmarked unless otherwise specified and/or requested. For more detailed information regarding marked product and how to request this option, please contact KEMET.

KEMET Electronic Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicated or that other measures may not be required.