



MG Paint About MG links contact us

home MSDS products distributors tech support downloads

Part Number/Keyword

print

RoHS COMPLIANT

RTV Silicones by MOMENTIVE™

RTV 160

RTV160

SPECIAL ORDER

BUY NOW

Description **Technical Data** MSDS FAQ Resources

Use Adhesive Sealant

Special Feature Non-corrosive

Standards UL HB Recognition

Cross Reference RTV160

GE Silicone National Stock Number

5970-00-110-8234

5970-01-081-1733

8040-00-927-1513

Uncured Properties

Consistency Pourable

Color White

Specific Gravity 1.04

Tack Free Time 4 hours

Cure through time 48 hours

Useful Temp. Range -60°C to 205°C (-75°F to 400°F)

Cured Properties - MECHANICAL

Hardness 25 (Shore A)

Tensile Strength 3.73 MPa (550 psi)

Elongation 400%

Cured Properties - ELECTRICAL

Dielectric Strength 20 kV/mm (500 V/mil)

Dielectric Constant 2.8 @ 60 Hz

Other

Viscosity (@ 25°C) 38,000 cps

ALL MG PRODUCTS ▾

- + Dusters & Cold Sprays
- + Cleaning Products for Electronics
- + Protective Coatings
- + Adhesives
- + Greases and Lubricants
- + Prototyping and Circuit Repair
- + Solder and Solder Related Products
- RTV Silicones
 - Adhesives / Sealants**
 - Potting Compounds
 - Primers
- + Epoxies
- Specialty Products
- + 3D Printing



© 2000 - 2014 MG Chemicals. All rights reserved.

[Site Map](#) [Terms & Conditions](#) [Contact Us](#) [Careers](#)